



- Liner:** 76lb polycoated kraft, differential silicone treated on both sides
- Liner Side Adhesive:** Non-irritating medical-grade acrylic (M121)
- Backing/Carrier:** 0.5 mil Polyester Film
- Air Side Adhesive:** Non-irritating medical-grade acrylic (M121)

Applications

- Diagnostic test strips and devices
- Surgical drape fabrication and assembly
- Medical device assembly
- Surgical drape attachment: drape to drape, drape to skin
- Medical device attachment

Features

Benefits

- | | |
|---|---|
| <ul style="list-style-type: none"> • Polyester Film Carrier • Non-Irritating Acrylic Adhesive • Differential release liner | <ul style="list-style-type: none"> • Support for aid in processing and application • Conformable • High tack and good shear properties • Low flow and outgassing • Good dimensional stability • Excellent for die-cutting • Moisture resistant |
|---|---|

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness w/liner	8.7 mils	0.221 mm	PSTC 133
Adhesive Thickness (Air Side)	1.3 mils	0.033 mm	PSTC 133
Adhesive Thickness (Liner Side)	1.3 mils	0.033 mm	PSTC 133
Carrier Thickness	0.5 mils	0.013 mm	PSTC 133
Liner Thickness	5.6 mils	0.142 mm	PSTC 133
Adhesion to Steel (Air Side)	50 oz/in	5.47 N/cm	PSTC 101 Mod
Adhesion to Steel (Liner Side)	60 oz/in	6.56 N/cm	PSTC 101 Mod

Product Safety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic, non-sensitizing, and non-irritating.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.