


3426A

Transfer Adhesive



Adhesive: Rubber-Based (M104)

Liner: 60lb bleached kraft, silicone treated on

both sides with differential release

Applications

- Mounting and laminating electronic components
- Medical device component
- Patient monitoring

- Medical device assembly
- Sensor components
- Pulse oximetry

Features Benefits

Rubber Adhesive	Superior adhesion to various materials for		
	component assembly		
60lb Release Liner	Easy liner removal		

Typical Test Values

	Standard UOM	Metric UOM	Test Method		
Total Thickness w/liner	5.3 mils	0.135 mm	PSTC 133		
Adhesive Thickness	1.8 mils	0.046 mm	PSTC 133		
Liner Thickness	3.5 mils	0.089 mm	PSTC 133		
Adhesion to Steel	170 oz/in	18.60 N/cm	PSTC 101 Mod		
Liner Release	70 g/in	0.27 N/cm	ASTM D-5375		
Product Safety					

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic and non-irritating.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

