


3599A

Transfer Adhesive



Adhesive: Medical-grade acrylic (M116)

Liner: 4 mil PET Film, silicone treated on both

sides

Applications

Medical device attachment

Medical device assembly

Features Benefits

Acrylic Adhesive	Excellent adhesion to skin	
	 Good balance of shear, tack, and adhesion 	
PET Fil Liner	 Excellent lay flat and dimensional stability 	
	 Easy to die-cut 	

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness w/liner	5.1 mils	0.130 mm	PSTC 133
Adhesive Thickness	1.1 mils	0.028 mm	PSTC 133
Liner Thickness	4.0 mils	0.102 mm	PSTC 133
Adhesion to Steel	64 oz/in	7.00 N/cm	PSTC 101 Mod

Product Safety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be non-cytotoxic, non-sensitizing, and non-irritating.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

