



| Release Liner Liner Side Adhesive Carrier Air Side Adhesive | Liner: | 74lb polycoated bleached kraft, silicone treated on both sides |
|--|------------------|--|
| | LS Adhesive: | Medical-Grade Acrylic (M116) |
| | Backing/Carrier: | 0.5 mil polyester film |
| | AS Adhesive: | Medical-Grade Acrylic (M116) |

Applications

Medical device assembly

• Medical device attachment

| Features | Benefits |
|------------------------|--|
| Polyester Film Carrier | Support for aid in processing and applicationEasily conforms to various surface types |
| Acrylic Adhesive | Excellent adhesion to skinGood balance of shear, tack, and adhesion |
| 74lb PC Bleached Kraft | Easy to die cut and processGood dimensional stability and moisture resistance |

Typical Test Values

| | Standard UOM | Metric UOM | Test Method | | | |
|---------------------------------|--------------|------------|--------------|--|--|--|
| Total Thickness w/liner | 8.8 mils | 0.224 mm | PSTC 133 | | | |
| Adhesive Thickness (Air Side) | 1.2 mils | 0.030 mm | PSTC 133 | | | |
| Carrier Thickness | 0.5 mils | 0.013 mm | PSTC 133 | | | |
| Adhesive Thickness (Liner Side) | 1.2 mils | 0.030 mm | PSTC 133 | | | |
| Liner Thickness | 5.9 mils | 0.150 mm | PSTC 133 | | | |
| Adhesion to Steel (Air Side) | 65 oz/in | 7.11 N/cm | PSTC 101 Mod | | | |
| Adhesion to Steel (Liner Side) | 65 oz/in | 7.11 N/cm | PSTC 101 Mod | | | |
| Dra duat Cafata | | | | | | |

Product Safety

The base adhesives in this medical product have been tested in accordance with ISO 10993 and found to be noncytotoxic, non-sensitizing, and non-irritating.

In accordance with FDA cGMP requirements, Berry reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.berryglobal.com