





Backing:1.0 mil White Polyester FilmAdhesive:Heat Seal Rubber (1905)Liner:60lb semi-bleached kraft, silicone
release treated on both sides

Labelling applications

Applications

 Ideal for heat seal labels for books and periodicals

Features	Benefits	
Polyester Film Backing	Conformable and printable	
	 Resists tearing and abrasion 	
Heat Seal Rubber Adhesive	 Excellent aging characteristics and shelf life after proper heat seal bonding 	
60lb Liner	Easy to process and die-cut	

Typical Test Values

	71		
	Standard UOM	Metric UOM	Test Method
Total Thickness w/liner	6.5 mils	0.165 mm	PSTC 133
Adhesive Thickness	2.0 mils	0.051 mm	PSTC 133
Carrier Thickness	1.0 mils	0.025 mm	PSTC 133
Liner Thickness	3.5 mils	0.089 mm	PSTC 133
Adhesion to Steel	60 oz/in	6.56 N/cm	PSTC 101 Mod
Application Temperature	40 to 150 °F	4 to 65 °C	
Laminating Temperature	200 to 260 °F	93 to 127 °C	
Maximum Continuous Use	160 °F	71 °C	
Intermittent Use	180 °F	82 °C	

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.berryglobal.com