


7833-PET

Acrylic Transfer Tape



Release Liner

Liner:

1.5 mil Clear PET

Adhesive

Adhesive:

Acrylic (I639)

Applications

- Laminating and bonding to ether and ester foams and low-perm urethane foams
- Applications requiring a higher heat resistance
- Applications requiring resistance to microbial growth

Features

- Acrylic Adhesive
- PET Film Liner

Benefits

- Excellent adhesion to a wide variety of substrates
- Engineered for foam-to-foam bonding
- High temperature resistance
- Good shear strength
- Resistance to plasticizers
- Improved die-cutting and kiss cutting
- Smooth, clean removal

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Adhesive Thickness	3.0 mils	0.076 mm	PSTC 133
Liner Thickness	1.5 mils	0.038 mm	PSTC 133
Adhesion to Steel	60 oz/in	6.56 N/cm	PSTC 101 Mod - 1 mil PET
Adhesion to Steel	165 oz/in	18.05 N/cm	PSTC 101 Mod - 2 mil Alu Foil
Shear Strength (at 72 °F)	7 Days		PSTC 107 Mod
Laminating Temperature	68 to 100 °F	20 to 38 °C	
Service Temperature	-30 to 250 °F	-34 to 121 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.