


Double-Coated Tape



Liner: 74lb semi-bleached polycoated kraft, silicone release coated on both sides

Liner Side Adhesive: Acrylic (I600)

Backing/Carrier: 0.5 mil polyester film

Air Side Adhesive: Acrylic (I600)

Applications

- Graphic arts and decals
- Mounting nameplates, decals, and plastic trim
- Laminating paper, felt, sponge rubber, foam, and plastics

Features

- Polyester Film Carrier
- Acrylic Adhesive

Benefits

- Support for aid in processing and application
- Conformable
- Excellent anchorage to rubber and plastic sponge
- Resists plasticizer and oil migration
- UV resistant with excellent aging characteristics
- Easy to die-cut and process

- 74lb Semi-bleached Kraft Liner

Typical Test Values

	Standard UOM	Metric UOM	Test Method
Total Thickness w/liner	10.4 mils	0.264 mm	PSTC 133
Adhesive Thickness (Air Side)	2.0 mils	0.051 mm	PSTC 133
Adhesive Thickness (Liner Side)	2.0 mils	0.051 mm	PSTC 133
Carrier Thickness	0.5 mils	0.013 mm	PSTC 133
Liner Thickness	5.9 mils	0.150 mm	PSTC 133
Adhesion to Steel (Air Side)	55 oz/in	6.02 N/cm	PSTC 101 Mod
Adhesion to Steel (Liner Side)	55 oz/in	6.02 N/cm	PSTC 101 Mod
Shear Strength (Air Side)	168+ hours		PSTC 107
Shear Strength (Liner Side)	168+ hours		PSTC 107
Application Temperature	32 to 180 °F	0 to 82 °C	
Laminating Temperature	60 to 250 °F	16 to 121 °C	
Maximum Continuous Use	200 °F	93 °C	
Intermittent Use	250 °F	121 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.