





Liner:	60lb semi-bleached kraft, differential silicone treated on both sides
Liner Side Adhesive:	Acrylic (1615)
Backing/Carrier:	0.5 mil Polvester Film
bucking/cumer.	
Air Side Adhesive:	Rubber (1900)

Temporary mounting applications requiring

## **Applications**

٠

- Sealing polybags and packaging resealable
- Laminating paper, plastic, foam, and metal
- Component assembly and attachment

Features	Benefits		
Polyester Film Carrier	<ul><li>Support for aid in processing and application</li><li>Conformable</li></ul>		
Differential Adhesive System	<ul> <li>Air-side acrylic bonds aggressively even to low energy materials</li> <li>Low peel liner side adhesive provides resealable capability and clean removal</li> </ul>		
60lb Differential release liner	Excellent for die-cutting		

• Easy liner removal

clean removal

## **Typical Test Values**

	Standard UOM	Metric UOM	Test Method
Total Thickness w/liner	5.7 mils	0.145 mm	PSTC 133
Adhesive Thickness (Air Side)	1.1 mils	0.028 mm	PSTC 133
Adhesive Thickness (Liner Side)	0.6 mils	0.015 mm	PSTC 133
Carrier Thickness	0.5 mils	0.013 mm	PSTC 133
Liner Thickness	3.5 mils	0.089 mm	PSTC 133
Adhesion to Steel (Air Side)	90 oz/in	9.85 N/cm	PSTC 101 Mod
Adhesion to Steel (Liner Side)	35 oz/in	3.83 N/cm	PSTC 101 Mod

## **Product Safety**

In accordance with FDA cGMP requirements, Berry Global reminds the customer that ultimate fitness for use must be determined by the manufacturer of the finished device.

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fifness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.



25 Forge Pkwy Franklin, MA 02038 1-800-343-7875 Fax 1-800-328-4822 www.berryglobal.com