
POLYKEN[®] **3577C**

Liner:

Double-Coated Closed Cell Foam Tape



4 mil polyester, silicone treated on both sides

Benefits

Liner Side Adhesive Rubber based adhesive (M117)

Medical device attachment

1/32" white, closed cell crosslinked **Backing/Carrier:** polyethylene foam

Air Side Adhesive: Non-sensitizing acrylic adheisve (M109)

Applications

- Electrodes: ECG, EKG, TENS
- Medical device assembly

Features

| • | Foam Carrier | | Soft and flexible for maximum patient comfort Conformable and easily adapts to medical devices and body contours |
|---|---|---|--|
| • | Air-Side Non-Sensitizing Acrylic Adhesive | | High tack and good shear strength Stable to EtO and gamma sterilization |
| • | Liner-Side Rubber Based Adhesive | ٠ | High shear and good adhesion properties |
| • | Polyester Release liner | | Excellent lay flat and dimensional stability Easily die-cut |

Typical Test Values

| | Standard UOM | | Metric | UOM | Test Method | | | | |
|---------------------------------|--------------|-------|----------|------|--------------|--|--|--|--|
| Total Thickness w/liner | 40.25 | mils | 1.022 | mm | PSTC 133 | | | | |
| Adhesive Thickness (Air Side) | 2.5 | mils | 0.064 | mm | PSTC 133 | | | | |
| Adhesive Thickness (Liner Side) | 2.5 | mils | 0.064 | mm | PSTC 133 | | | | |
| Carrier Thickness | 31.25 | mils | 0.794 | mm | PSTC 133 | | | | |
| Liner Thickness | 4.0 | mils | 0.1 | mm | PSTC 133 | | | | |
| Adhesion to Steel (Air Side) | 210 | oz/in | 22.97 | N/cm | PSTC 101 Mod | | | | |
| Adhesion to Steel (Liner Side) | 210 | oz/in | 22.97 | N/cm | PSTC 101 Mod | | | | |
| | | Produ | ct Safet | V | | | | | |

The base adhesives utilized in this medical product has been tested in accordance with ISO 10993 and found to be noncytotoxic, non-sensitizing, and non-irritating.

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.



101 Oakley Street Evansville, IN 47710 1-800-343-7875 Fax 1-800-328-4822 www.berryglobal.com