


## Differential Double-Coated Tape



- Liner:** 80lb super calendered kraft with differential release
- Liner Side Adhesive:** Acrylic (I610)
- Backing/Carrier:** 0.5 mil polyester film
- Air Side Adhesive:** Rubber (I903)

### Applications

- Mounting and assembly applications
- Laminating to paper, plastic, foam, and metal
- Packaging applications

### Features

- Polyester Film Carrier
- Air-Side Rubber Adhesive
- Liner-Side Acrylic Adhesive
- 80lb SCK Differential Release Liner

### Benefits

- Support for aid in processing and application
- Easily conforms to various surface types
- Excellent adhesion to PE as well as low surface energy materials
- Permanent bond
- Easy, no-residue removal
- Die-cutttable

### Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Total Thickness w/liner</b>	7.8 mils	0.198 mm	PSTC 133
<b>Adhesive Thickness (Air Side)</b>	1.7 mils	0.043 mm	PSTC 133
<b>Carrier Thickness</b>	0.5 mils	0.013 mm	PSTC 133
<b>Adhesive Thickness (Liner Side)</b>	0.8 mils	0.020 mm	PSTC 133
<b>Liner Thickness</b>	4.8 mils	0.122 mm	PSTC 133
<b>Liner Release</b>	200 g/in	0.77 N/cm	ASTM D-5375
<b>Adhesion to Steel (Air Side)</b>	75 oz/in	8.21 N/cm	PSTC 101 Mod
<b>Adhesion to Steel (Liner Side)</b>	20 oz/in	2.19 N/cm	PSTC 101 Mod
<b>Shear Strength (Air Side)</b>	90+ hours		PSTC 107
<b>Shear Strength (Liner Side)</b>	40 hours		PSTC 107
<b>Laminating Temperature</b>	50 to 150 °F	10 to 65 °C	
<b>Maximum Continuous Use</b>	160 °F	71 °C	
<b>Intermittent Use</b>	180 °F	82 °C	

Recommended Storage Conditions: 40-60% Humidity, 60°F-80°F

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.