


# 7336A

## Rubber Transfer Tape



Release Liner

Liner:

74# Polycoated Kraft

Adhesive

Adhesive:

Rubber (I917)

### Applications

- Laminating and bonding for urethane and polyethylene foams, felts, fabrics, and rigid plastics
- Ideal for temporary hold in place applications
- Permanent bonding in low-stress applications
- Automotive, graphic arts, HVAC, gasketing and general bonding

### Features

- Rubber Adhesive
- 74# Polycoated Kraft Liner

### Benefits

- High peel strength
- Excellent initial tack
- Moderate shear strength
- Conformable and good dimensional stability

### Typical Test Values

	Standard UOM	Metric UOM	Test Method
<b>Adhesive Thickness</b>	1.4 mils	0.036 mm	PSTC 133
<b>Liner Thickness</b>	5.5 mils	0.140 mm	PSTC 133
<b>Adhesion to Steel</b>	144 oz/in	15.75 N/cm	PSTC 101 Mod - 1 mil PET
<b>Loop Tack</b>	160 oz/in	17.50 N/cm	PSTC 16
<b>Shear Strength (at 72 °F)</b>	24 Hours		PSTC 107 Mod
<b>Laminating Temperature</b>	68 to 100 °F	20 to 38 °C	
<b>Service Temperature</b>	30 to 150 °F	-1 to 66 °C	

Recommended Storage Conditions: 40-60% Humidity, 60 °F - 80 °F

Standard Shelf Life: 12 months from date of shipment

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To BERRY's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.